

Diâmetro		Schedule 5		Schedule 10		Schedule 40 C/C e S/C		Schedule 80 s/c		Schedule 160 s/c	
pol.	mm	Espeçura	Peso Teórico	Espeçura	Peso Teórico	Espeçura	Peso Teórico	Espeçura	Peso Teórico	Espeçura	Peso Teórico
		mm	kg/m	mm	kg/m	mm	kg/m	mm	kg/m	mm	kg/m
1/2"	21,3	1,65	0,817	2,11	1,02	2,77	1,26	3,73	1,62	4,78	1,95
3/4"	26,7	1,65	1,038	2,11	1,30	2,87	1,68	3,91	2,19	5,56	2,9
1"	33,4	1,65	1,317	2,77	2,13	3,38	2,5	4,55	3,23	6,35	4,24
1.1/4"	42,2	1,65	1,68	2,77	2,74	3,56	3,38	4,85	4,46	6,35	5,61
1.1/2"	48,3	1,65	1,933	2,77	3,16	3,68	4,05	5,08	5,4	7,14	7,25
2"	60,3	1,65	2,434	2,77	4	3,91	5,43	5,54	7,47	8,74	11,11
2.1/2"	73	2,11	3,762	3,05	5,37	5,16	8,62	7,01	11,4	9,53	14,92
3"	88,9	2,11	4,604	3,05	6,58	5,49	11,28	7,62	15,25	11,13	21,35
3.1/2"	101,6	2,11	5,277	3,05	7,55	5,74	13,56	8,08	18,6	-	-
4"	114,3	2,11	5,951	3,05	8,53	6,02	16,06	8,56	22,29	13,49	33,54
5"	141,3	2,77	9,647	3,40	11,78	6,55	21,75	9,52	30,92	15,88	49,11
6"	168,3	2,77	11,526	3,40	14,09	7,11	28,23	10,97	42,51	18,26	67,56
8"	219,1	2,77	15,063	3,76	20,35	8,18	42,48	12,7	64,56	23,01	111,27
10"	273,05	3,4	23,049	4,19	28,32	9,27	60,23	15,1	95,87	28,58	172,33
12"	323,84	3,96	31,846	4,57	36,68	10,31	79,64	17,47	131,88	33,32	238,48



AO INOXIDÁVEL
 Série 300



AO CARBONO E INOXIDÁVEL
 (Demais ligas consultar)

